

(1)

1.

1.1 100%

Ne 24, 25, 26, 27, 60 (Lawn), (Sateen),

Ne 28, 29, 80 (Lawn),

Ne 30, 120 (Broad)

1.2

P/C Ne 65, 72

P/R Ne 66/2, 60

P/Ra Ne 40, 34

2.

2.1 Filament

Polyester : 75D Amungen, 가 1500/2, Trapical, 가 100D, Kashmir

Nylon : 50D, De Chine Crepe, 75D, Taffeta, 110D, Taffeta

1. Ne 60 (Lawn)

Corn Starch 5.5%

PVA 217 3.0%

Marpozol T-30	0.4%
Maconol H	0.6%
Neocintol C	0.02%

2. Ne 60 (Lawn)

Corn Starch	3.5%
PVA GH - 17	5.0%
Solgum T-1500	1.0%
Solvil Wax SX-135A	0.4%

3. Ne 60 (Sateen)

Corn Starch	3.5%
PVA GH - 18	5.0%
Solgum T-1500	1.0%
Maconol TS-253	0.4%
Neocintol C	0.03%

4. Ne 60

Corn Starch	4.0%
PVA 217	6.5%
Marpozol T-30	0.6%
Maconol H	1.2%
Neocintol C	0.02%

5. Ne 80

Corn Starch	5.0%
PVA GH - 17	8.0%
Marpozol T-30	1.0%
Maconol B-19	0.8%

6. Ne 80 (Sateen)

Corn Starch	5.5%
PVA B - 17	3.0%
Marpozol T-30	0.4%
Maconol H	0.9%
Neocintol C	0.01%

7. Ne 120/2 (Broad)

Corn Starch	4.5%
PVA GH - 17	1.5%
Marpozol T-30	0.6%
Neocintol C	0.03%

8. Polyester 가 75D/Kashmir(Slasher)

PVA 205	5.5%
Solgum T-2200	6.5%
Solvil Wax L-75	0.2%

9. Polyester 가 75D Amungen(Slasher)

PVA -05	5.0%
Saivinol A-750	3.0%
Solvil Wax L-75	0.2%

10. Polyester 가 75D/2 Trapical(Slasher)

PVA 205	5.0%
Marpozol S-50	1.5%
Marpozol TM-100	2.5%
Tomenolin F	0.5%
Sizing Silicon #20	0.1%

11. Polyester 가 150D Trapical(Warping Sizer)

PVA GL-05	4.5%
Solgum V-333	7.5%
Solvil Wax L-75	0.2%

12. Polyester 가 100D Kashmir(Warping Sizer)

PVA 205	6.0%
Plus Size	4.0%
Saitex T-190	0.2%
Lubricant 205	0.02%

13. Nylon 50D De Chine, Crepore(Slasher)

PVA GL-05	6.5%
Saivinol - A-750	1.0%
Saitex Silicone	0.2%

14. Nylon 110D Taffeta (Warping Sizer)

PVA GL-05	6.5%
Solgum 2200	0.5%
Lubricant 205	0.2%

15. Nylon 70D Taffeta Crepone (Warping Sizer)

PVA 205	6.0%
Plus Size 350	0.5%
Saitex 24	0.2%
Satex Silicone 53	0.2%

16. Polyester/ Ne 65 Sateen

Corn Starch	3.0%
PAV 217	6.0%
Marpozol T-30	1.0%
Solvil Wax SX-135A	0.5%

17. Polyester/	Ne 65 Lawn
Corn Starch	7.0%
PVA 217	4.0%
Marpozol T-30	1.0%
Maconal B-19	0.8%
Neocintol C	0.03%

18. Polyester/	Ne 72 Lawn
Corn Starch	3.0%
PVA GH-17	5.7%
Solgum T-1500	3.5%
Solvil Wax FX-H	1.0%

19. Polyester/Polynosic	Ne60 Lawn
Corn Starch	5.0%
PVA GH-17	5.7%
Maconol TS-253	0.3%

20. Polyester/Rayon	Ne 66/2 Kashmir
PVA 217	2.0%
Solgum T-1500	6.0%

21. Polyester/Ramie	40 Shirts
Corn Starch	3.0%
PVA GH-17	5.0%
Acrylon F-164	1.5%
Maconol TS-253	0.7%

22. Polyester/Ramie	Ne 34
Corn Starch	2.0%
PVA 217	4.5%
Marpozol T-30	2.0%
Maconol B-19	0.4%

)

Marpozol T-30 : Anion, ,

Maconol B-19 : Sizing (Hot Size), Novion, ,

Neocintol C : PCP가

Solgum T-1500 :

Solvil Wax SX-135A :

Maconol H : Anion

Maconol TS-253 :